

TECHNICAL INFORMATION

Revision: 1
Date: 14.09.2014
Page: 1/2

NEWOTEC[®] 318

Product Category:	Dispersing agent for PVC pastes												
Fields of Application:	Filled PVC formulations, especially with high filler load												
Product Characteristics:	<ul style="list-style-type: none">➤ optimized for low VOC applications➤ good colour stability➤ free of APEO and phthalates➤ additional viscosity reducing effect												
Chemical Composition:	Mixture containing long-chain fatty acid esters and phosphate esters												
Technical Data:	<table><tr><td>Appearance (20 °C):</td><td>colourless - yellowish liquid</td></tr><tr><td>Active content:</td><td>100%</td></tr><tr><td>Flash point:</td><td>>120 °C</td></tr><tr><td>Boiling range:</td><td>>250 °C</td></tr><tr><td>Solidification range:</td><td>Approx. 5-10°C</td></tr><tr><td>Compatibility:</td><td>compatible with all commonly used PVC paste formulations within the recommended concentration range</td></tr></table>	Appearance (20 °C):	colourless - yellowish liquid	Active content:	100%	Flash point:	>120 °C	Boiling range:	>250 °C	Solidification range:	Approx. 5-10°C	Compatibility:	compatible with all commonly used PVC paste formulations within the recommended concentration range
Appearance (20 °C):	colourless - yellowish liquid												
Active content:	100%												
Flash point:	>120 °C												
Boiling range:	>250 °C												
Solidification range:	Approx. 5-10°C												
Compatibility:	compatible with all commonly used PVC paste formulations within the recommended concentration range												
Storage:	<table><tr><td>Shelf life:</td><td>in originally sealed drums, approximately one year from the date of delivery under the conditions recommended below</td></tr><tr><td>Storage Conditions:</td><td>Recommended storage temperature: min +3°C, max +40 °C Protect from moisture Frost resistant</td></tr></table>	Shelf life:	in originally sealed drums, approximately one year from the date of delivery under the conditions recommended below	Storage Conditions:	Recommended storage temperature: min +3°C, max +40 °C Protect from moisture Frost resistant								
Shelf life:	in originally sealed drums, approximately one year from the date of delivery under the conditions recommended below												
Storage Conditions:	Recommended storage temperature: min +3°C, max +40 °C Protect from moisture Frost resistant												
Packaging:	drum / IBC												
Use concentration:	<table><tr><td>lowest:</td><td>1% referring to the weight of the <u>filler</u> content</td></tr><tr><td>highest:</td><td>4 phr in the paste</td></tr></table> <p>We strongly recommend to carry out own lab tests in order to determine the optimum dosage, especially when more than 4 phr are added.</p>	lowest:	1% referring to the weight of the <u>filler</u> content	highest:	4 phr in the paste								
lowest:	1% referring to the weight of the <u>filler</u> content												
highest:	4 phr in the paste												

NEWOTEC[®] 318

Application:

NEWOTEC[®] 318 must be added to the liquid components during the preparation of the paste. The paste will then maintain a reduced viscosity when the filler and other solid ingredients are added.

NEWOTEC[®] 318 leads to a homogeneous dispersion of solids in the paste, prevents the formation of agglomerates and guarantees a free-flowing paste in production.

Further Information:

NEWOTEC[®] 318 has a good colour stability and does not significantly affect the heat stability of common PVC paste formulations under common processing conditions.

NEWOTEC[®] 318 has an additional viscosity reducing effect which is much stronger compared to pure dispersants.

The data in this technical information are derived from practical experience. They do not guarantee specific product properties or the suitability of the product for particular applications. Lab or pilot tests should be carried out in any case. Due to many different possible process conditions we cannot assume any liability. Any existing industrial patent rights have to be respected. Additional information on product properties pertaining to working safety as well as environmental protection can be found in the material safety data sheet.